

TYPICAL PROPERTIES OF
HyPUR-cel® T1505

POLYMER

POLYURETHANE

FLAMMABILITY

FMVSS-302

PASS (.079" OR THICKER)¹

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
DENSITY	ASTM D 3574	lb/ft ³ kg/m ³	13 - 17 208 - 272
HARDNESS	ASTM D2240	SHORE O	6
TENSILE STRENGTH	ASTM D3574	psi kPa	60 (MIN) 413 (MIN)
ELONGATION	ASTM D3574	%	200 (MIN)
TEAR STRENGTH	ASTM D624	lb/in kN/m	9 (MIN) 1.6 (MIN)
COMPRESSION SET 50% - 22 HRS @ 73°F	ASTM D1056	%	3 (MAX)
COMPRESSION FORCE DEFLECTION 25%	ASTM D3574	psi kPa	2 - 6 13.8 - 41.4
COMPRESSION DEFLECTION @ 25%	ASTM D1056	psi kPa	3 - 7 20.7 - 48.3
COLOR	N/A	N/A	BLACK

¹ Submit request for any thickness below .079".

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

Issue 5 10/31/05