

TYPICAL PROPERTIES OF
Ensolite® SCC

POLYMER

PVC/NBR

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT	SPECIFICATIONS
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	9 - 15 62 - 103.4	ASTM D1056-07.....2C3 / 2C4 ASTM D1056 Suffix's.....B2, C1, F1, M
DENSITY	ASTM D1056	pcf g/cm ³	10 - 15 .160 - .240	
COMPRESSION SET (MAX)	ASTM D1056	%	20	
WATER ABSORPTION (MAX)	ASTM D1056	%	5	
TENSILE STRENGTH (MIN)	ASTM D412 (DIE A)	psi kPa	150 1034	
ELONGATION (MIN)	ASTM D412 (DIE A)	%	125	
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30	
COLOR	N/A	N/A	GREY / NATURAL	
				FLAMMABILITY SPECIFICATIONS
				FMVSS-302.....PASS
				ADDITIONAL INFORMATION
				Service Temperature -40°F to 200°F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728
TELEPHONE (304) 525-3116 • FAX (304) 523-4316
WWW.RUBBERLITE.COM

Issue Date: 3/5/12